



INVESTOR IN PEOPLE

USA
The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.




Signed

Stephen Hordley

Dated 9 September 2003

OLIFF & BERRIDGE, PLC
P.O. BOX 19928
ALEXANDRIA, VA 22320
(703) 836-6400
APPLICANT: Mark Henry SHIPTON et al.
APPLICATION NO.: New U.S. Application
FILED: October 2, 2003
FOR: METHOD OF FORMING A DIFFUSION BARRIER ON A
METALLIC SUBSTRATE
ATTORNEY DOCKET NO.: 117313

Patents Form 1/77

Patents Act 1977
(Rule 16)21OCT02 E757018-1 001097
P01/7700 0:00-0224301.2**Request for grant of a patent***(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)*

The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

1. Your reference PAT/AT/3030

2. Patent application number
(The Patent Office will fill in this part)

0224301.2

21 OCT 2002

3. Full name, address and postcode of the or of each applicant *(underline all surnames)*ROLLS-ROYCE plc
65 BUCKINGHAM GATE
LONDON
SW1E 6AT
GREAT BRITAINPatents ADP number *(if you know it)*

3970002

If the applicant is a corporate body, give the country/state of its incorporation

GREAT BRITAIN

4. Title of the invention METHOD OF FORMING A DIFFUSION BARRIER ON A METALLIC SUBSTRATE

5. Name of your agent *(if you have one)*MR V J BIRD
INTELLECTUAL PROPERTY DEPT WH 58
ROLLS-ROYCE plc
PO BOX 3
FILTON
BRISTOL
BS34 7QE"Address for service" in the United Kingdom to which all correspondence should be sent *(including the postcode)*Patents ADP number *(if you know it)*

65789006

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and *(if you know it)* the or each application number

Country

Priority application number
*(if you know it)*Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
*(day / month / year)*8. Is a statement of inventorship and of right to grant of a patent required in support of this request? *(Answer 'Yes' if*

YES

a) any applicant named in part 3 is not an inventor, or
b) there is an inventor who is not named as an applicant, orc) any named applicant is a corporate body.
See note (d))

Patents Form 1/77

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form 0

Description 12 ✓

Claim(s) 3 ✓ *CF*

Abstract 1 ✓

Drawing(s) 0

10. If you are also filing any of the following, state how many against each item.

Priority documents 0

Translations of priority documents 0

Statement of inventorship and right to grant of a patent (Patents Form 7/77) YES

Request for preliminary examination and search (Patents Form 9/77) YES

Request for substantive examination (Patents Form 10/77) NO

Any other documents (please specify) NO

11.

I/We request the grant of a patent on the basis of this application.

Signature

Date

V J BIRD

17 OCTOBER 2002

12. Name and daytime telephone number of person to contact in the United Kingdom

DR ADAM TINDALL 0117 979 4623
adam.tindall@rolls-royce.com

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

Patents Form 1/77

Patents Form 7/77 THE PATENT OFFICE

Patents Act 1977
(Rule 15)

21 OCT 2002

RECEIVED BY FAX



Statement of inventorship and of right to grant of a patent

The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

1. Your reference PAT/AT/3030

2. Patent application number
(if you know it)

0224301.2

21 OCT 2002

3. Full name of the or of each applicant ROLLS-ROYCE plc

4. Title of the invention

METHOD OF FORMING A DIFFUSION BARRIER ON A METALLIC SUBSTRATE

5. State how the applicant(s) derived the right
from the inventor(s) to be granted a patentBY VIRTUE OF THE INVENTORS' TERMS AND CONDITIONS OF
EMPLOYMENT6. How many, if any, additional Patents Forms
7/77 are attached to this form?
(see note (c))

NO

7.

I/We believe that the person(s) named over the page (and on
any extra copies of this form) is/are the inventor(s) of the invention
which the above patent application relates to.

Signature

Date

V J BIRD

17 OCTOBER 2002

8. Name and daytime telephone number of
person to contact in the United KingdomDR ADAM TINDALL 0117 979 4623
adam.tindall@rolls-royce.com

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there are more than three inventors, please write the names and addresses of the other inventors on the back of another Patents Form 7/77 and attach it to this form.
- When an application does not declare any priority, or declares priority from an earlier UK application, you must provide enough copies of this form so that the Patent Office can send one to each inventor who is not an applicant.
- Once you have filled in the form you must remember to sign and date it.

Patents Form 7/77

0050354 21-Oct-02 11:31

Patents Form 7/77

Enter the full names, addresses and postcodes of the inventors in the boxes and underline the surnames

MARK HENRY SHIPTON
14 SWEETS ROAD
KINGSWOOD
BRISTOL
BS15 1XJ

Patents ADP number (if you know it): 8025678001

TERENCE WALTER MABER
10 PEN PARK ROAD
SOUTHMEAD
BRISTOL
BS10 5SB

Patents ADP number (if you know it): 7944333001

MARTIN DEAKIN
17 COTSWOLD WAY
ASHBY DE LA ZOUCH
LE65 1ET

Patents ADP number (if you know it): 8488645001

Reminder

Have you signed the form?

Patents Form 7/77

- 1 -

DUPLICATE

METHOD OF FORMING A DIFFUSION BARRIER
ON A METALLIC SUBSTRATE

The present invention relates to a method of forming a platinum aluminide diffusion barrier on a metallic substrate, and an oxidation resistant metallic structure formed thereby. In one particularly preferred form of the invention, the metallic substrate is a titanium alloy, and the platinum aluminide diffusion barrier serves to protect the alloy against the damaging effects of α -case oxide formation in high temperature oxidative environments.

It is known to use a platinum aluminide intermetallic surface diffusion barrier to improve the oxidation and corrosion resistance of a metallic substrate without substantial detriment to the mechanical properties of the substrate, particularly in conditions of high temperature (eg above about 650°C).

WO-A-94/18359, the disclosure of which is incorporated herein by reference, discloses the formation of a platinum aluminide layer on a titanium substrate by sequential deposition of a platinum layer followed by an aluminium layer. This two-layer deposited system is then subjected to a reaction treatment consisting of heating the deposited materials under moderate vacuum for a period of two hours at a temperature of 750°C, causing the formation of a platinum aluminide diffusion barrier. Deposition of the layers is stated to be by RF biased DC sputtering.

The sputtering technique suffers from the disadvantage that it is not usable where the substrate is a large metallic component. There remains a need for a method of forming a diffusion barrier on a metallic substrate which is generally applicable to articles of any size within a large range of sizes, from the order of millimetres to the order of metres.

The present invention is based on our surprising finding that a platinum aluminide diffusion barrier can conveniently be formed on a metallic substrate by applying the platinum and aluminium metallic starting materials entrained in an organic carrier. This

- 2 -

method has the advantages that it is quicker, less costly and may be applied to a much wider range of substrate sizes than the prior art methods.

According to a first aspect of the present invention, there is provided a method of forming a platinum aluminide diffusion barrier on a metallic substrate, the method comprising applying to the metallic substrate a coating comprising particulate platinum and particulate aluminium in an organic carrier and performing a reaction treatment on the thus applied platinum and aluminium which causes the platinum and the aluminium to form a diffusion barrier on the metallic substrate.

By the term "diffusion barrier", we mean a material overlying a surface of the metallic substrate, the material having a sufficiently low permeability to oxygen under the intended conditions of use of the substrate that oxygen is substantially prevented from contacting the metallic substrate from the surrounding atmosphere.

The coating may be applied to the metallic substrate in one or more application steps. If more than one application step is used, the components of the coating may be built up in the successive steps, eg by applying different materials in each step. It is preferred that the platinum and aluminium particles are applied as particles entrained in the organic carrier. A single composition entraining both metals in a desired molar ratio may be used, or separate compositions (eg each entraining one of the metals in a known concentration).

The metallic substrate preferably comprises an aerospace component or a portion thereof, eg a titanium alloy aerospace component or portion thereof.

According to a second aspect of the present invention, there is provided an oxidation resistant structure comprising a metallic substrate (eg a titanium alloy aerospace component or portion thereof) and a platinum aluminide diffusion barrier disposed thereon, wherein the structure is formed by the method according to the first aspect of the present invention.

- 3 -

According to a third aspect of the present invention, there is provided an oxidation resistant aerospace component comprising a metallic substrate and a substantially uniform platinum aluminide diffusion barrier disposed thereon, wherein the continuous area of the diffusion barrier is at least about 200 cm^2 , more particularly at least about 400 cm^2 , for example at least about 600 cm^2 .

The aerospace component according to the third aspect of the present invention is formable by the method of the first aspect, and is preferably formed using that method.

Preferably, the oxidation resistant structure or component exhibits substantially no diffusion of constituents of the diffusion barrier into the metallic substrate and substantially no detrimental reaction between constituents of the diffusion barrier and the metallic substrate.

The Metallic Substrate

The metallic substrate may comprise any metal or metal alloy and is suitably of relatively low density, for example less than about 7 gcm^{-3} , less than about 6 gcm^{-3} or less than about 5 gcm^{-3} . The metallic substrate suitably has a relatively high melting point or melting range. For example, the melting point or midpoint of the melting range may suitably be above about 1000°C , for example above about 1300°C , more preferably above about 1400°C , and most preferably above about 1500°C .

The metal substrate may comprise a first metal as the main component and any other suitable metal or metals as a further component or components. It will be appreciated that the metallic substrate may also comprise semi- and non-metallic components in addition to metallic components. These semi- and non-metallic components may typically be present in lower amounts than the main metallic component, for example less than about 5% by weight, less than about 3% by weight or less than about 1% by weight.

- 4 -

The main component of the metallic substrate preferably comprises a transition metal or a transition metal alloy. The metallic substrate preferably comprises titanium, an alloy of titanium, steel or stainless steel. In a preferred embodiment, the metallic substrate comprises a titanium alloy substantially in the beta form.

In the case where the metal substrate is a titanium alloy, it will comprise titanium as the main component and preferably one or more subsidiary components selected from the group consisting of aluminium, beryllium, bismuth, chromium, cobalt, gallium, hafnium, iron, manganese, molybdenum, niobium, nickel, oxygen, rhenium, tantalum, tin, tungsten, vanadium and zirconium. This alloy may also suitably comprise one or more semi- or non-metallic elements selected from the group consisting of boron, carbon, silicon, phosphorous, arsenic, selenium, antimony and tellurium. These elements may serve to increase the oxidation, creep or burning resistance of the metallic substrate.

Titanium may be present in such a titanium alloy in an amount greater than about 40% by weight, for example greater than about 50% by weight, greater than about 60% by weight or greater than about 70% by weight and in some embodiments may be present in an amount greater than about 80% by weight.

The amount in which the subsidiary component or components are present is determined by the use to which the metallic substrate will be put, as will be well understood by those skilled in this art. For example, the metallic substrate may be a ternary alloy comprising titanium, vanadium and chromium. Certain compositions of this type are especially preferred for certain applications wherein the titanium is present substantially in the beta form under most temperature conditions i.e. has less than about 3wt% alpha phase titanium, preferably less than about 2wt% alpha phase titanium. Such beta titanium alloys are based on ternary compositions of titanium-vanadium-chromium which occur in the titanium-vanadium-chromium phase diagram bounded by the points Ti-22V-13Cr, Ti-22V-36Cr, and Ti-40V-13Cr. These compositions are known to have useful mechanical properties such as high creep strength and a lack of combustibility at temperatures of up to at least about 650°C. In such compositions, the titanium is preferably present in an amount greater than about

- 5 -

40% by weight, for example greater than about 50% by weight. The chromium is preferably present in an amount greater than about 10% by weight, for example greater than about 15% by weight or greater than about 25% by weight. This concentration of chromium is necessary to provide the required non-burning characteristics of the alloy at these high temperatures. Vanadium may be present in an amount greater than about 20% by weight, for example greater than 25% by weight or greater than about 30% by weight. A specific alloy of this type has a composition comprising about 50wt% titanium, about 35wt% vanadium and about 15wt% chromium.

In other applications, the elements of the alloy composition will be significantly different. For example, the metallic substrate may comprise a quaternary or higher order alloy comprising titanium and other metals or semi-metals selected from the group consisting of aluminium, chromium, copper, iron, molybdenum, niobium, silicon, tin, vanadium and zirconium. In such alloys, aluminium is preferably present in an amount less than 10wt%, for example less than 8 wt%; chromium is preferably present in an amount less than 10wt%, for example less than 8wt%; copper is preferably present in an amount less than 5wt%, for example less than 3wt%; iron is preferably present in an amount less than 5wt%, for example less than 3wt%; molybdenum is preferably present in an amount less than 10wt%, for example less than 8wt%; niobium is preferably present in an amount less than 6wt%, for example less than 4wt%; silicon is preferably present in an amount less than 2wt%, for example less than 1wt%; tin is preferably present in an amount less than 16wt%, for example less than 12wt%; vanadium is preferably present in an amount less than 15wt%, for example less than 10wt%; and zirconium is preferably present in an amount less than 8wt%, for example less than 6wt%.

Titanium alloys are known to be generally susceptible to oxidation damage through the formation of the so-called α -case oxide layer. The diffusion barrier established according to the present invention is found to substantially restrict such oxidation damage in titanium alloys.

The Aerospace Component

- 6 -

Where the metallic substrate comprises an aerospace component or portion thereof, the component is preferably a component of an aero-engine which in use may be exposed to conditions of relatively high temperature (eg above about 400°C, particularly above about 650°C), eg casings, compressor drums, vanes, discs, blades, shafts, plugs or nozzles.

The Organic Carrier

The organic carrier provides a medium entraining the platinum or aluminium metal particles, enabling the particles to be applied in a generally uniform manner to the substrate surface.

The organic carrier preferably comprises relatively volatile components and relatively non-volatile components. The relatively volatile (fugitive) components serve to establish the desired physical properties of the carrier during the stage of application to the metallic substrate, and will subsequently evaporate off to leave a dry residue of the relatively non-volatile (binder) components, which will serve to bind the platinum and aluminium particles in intimate admixture on the surface of the metallic substrate for the reaction stage to form the intermetallic diffusion barrier.

The organic carrier is preferably liquid at room temperature. Its physico-chemical properties will be selected according to the specific conditions of use, as will be well understood by those of skill in this art.

For example, in addition to an appropriate balance of fugitive and binder components, the carrier may conveniently have a rheology (ie viscosity and thixotropy) providing good nozzle-non-blocking sprayability or good brush-, blade- or roller-spreadability onto the metallic substrate, resulting in good, uniform application to the substrate surface. The viscosity of the liquid carrier may be selected to restrict sedimentation of entrained metallic particles prior to use.

- 7 -

The surface tension of the organic carrier may, if desired, be adjusted by means of surfactants or tensides, to optimise the application performance of the carrier and the uniformity of the applied coating prior to reaction treatment to form the intermetallic diffusion barrier. Such adjustments will be well within the capability of those skilled in this art.

The organic carrier may be a single phase composition or a multiphase composition such as an emulsion. The carrier may optionally include water, for example 0 to about 30wt%, preferably 0 to about 20 wt%, of the organic carrier may be water. The composition comprising the carrier and the aluminium and platinum particles is suitably a dispersion or a colloidal suspension in the sense that the aluminium and platinum particles are dispersed throughout the solution.

The organic carrier preferably comprises one or more component selected from: esters, glycols, glycol ethers, polyhydric alcohols, polymeric alcohols, polymeric resins, aromatic hydrocarbons and esters or polymers of acrylic acid or methacrylic acid. Examples of suitable organic carrier materials include an alkoxy alkanol alkanoate in which each alkyl portion may independently have up to about 5 carbon atoms, such as 1-methoxy-2-propanol acetate; an alkylene glycol monoalkyl ether alkanoate in which each alkyl portion may independently have up to about 5 carbon atoms, such as ethylene glycol monobutyl ether acetate; an alkyl alkanoate in which each alkyl portion may independently have up to about 5 carbon atoms, such as butyl acetate; a polymeric resin such as an acrylic resin; an alkyl (meth) acrylate in which the alkyl portion may have up to about 5 carbon atoms, such as methyl methacrylate; an alkyl-substituted aromatic compound in which the alkyl portion may have up to about 5 carbon atoms, such as toluene; and any mixture thereof.

The major component of the organic carrier is preferably one or more organic esters. The ester component may suitably comprise up to about 70% by weight of the carrier, eg about 20 to about 65% by weight. The polymeric resin is preferably present in an amount of between about 1 and about 20% by weight. The remaining components, if

- 8 -

present, are preferably present in relatively small individual amounts, eg between about 0.01 and about 5% by weight for each component.

In a preferred embodiment, the carrier consists essentially of:

1 methoxy-2-propanol acetate (preferably 10-30 wt%)
ethylene glycol monobutyl ether acetate (preferably 10-30 wt%)
butyl acetate (preferably 10-30 wt%)
acrylic resin (preferably 5-10 wt%)
methyl methacrylate (preferably less than 0.1 wt%)
toluene (preferably less than 0.1 wt%).

The carrier medium may entrain: (i) platinum particles with aluminium particles in any desired molar ratio; (ii) platinum particles without aluminium particles, at any desired concentration of platinum; (iii) or aluminium particles without platinum particles, at any desired concentration of aluminium. Further details of the different modes of application of the different compositions are given below.

The calculation of the appropriate concentration of platinum and aluminium particles in the carrier medium will be well within the capability of those skilled in this art, having regard to the desired molar ratio of the particles in the dry residue of the coating for the reaction treatment. The platinum and the aluminium particles preferably comprise about 40 to about 60 % of the total weight of the respective composition in which they are present.

The Particulate Platinum and Aluminium

It is preferred that the platinum and aluminium particles not so large that they sediment easily on standing in the carrier medium or that formation of a good-quality intermetallic diffusion layer is hindered. The platinum and aluminium particles may preferably be substantially uniform and similar in size. The particles may typically have an average effective diameter greater than about 1µm, for example greater than 2µm. Normally,

- 9 -

the average particle size will be less than 20µm, for example less than 10µm, eg about 5µm. In the case of non-spherical particles, effective diameter is expressed as the "equivalent spherical diameter" of the particle, as will be well understood by those skilled in this art. Particle size may be measured by any technique commonly used in the art, for example dynamic light scattering or transmission electron microscopy.

Preparation of the Composition(s) for Application to the Metallic Substrate

The composition(s) comprising the organic carrier and the particulate platinum and/or aluminium are prepared by conventional mixing techniques, as will be well understood by those skilled in this art.

Application of the Composition(s) to the Metallic Substrate

The composition or compositions may be applied to the metallic substrate using any convenient application technique. Typically, spraying, brushing, blade-spreading or roller spreading may be used. In a particularly preferred embodiment, the composition(s) may be applied using a conventional aerosol spraying device comprising a nozzle through which the composition is delivered under pressure, whereby the composition forms an aerosol of fine dispersed droplets in the air.

The coating may be applied in one or more application steps. When more than one successive application step is used, the coating will preferably be built up in the successive steps, each step comprising application of a layer (preferably substantially uniform in thickness and continuous) constituting a portion of the coating.

It is preferred that the coating is applied as two layers; one layer comprising particulate platinum in a first organic carrier and the other comprising particulate aluminium in a second organic carrier. The first organic carrier may be the same or different from the second organic carrier. It is preferred that the layer comprising the aluminium particles is applied over the layer comprising the platinum particles. This is partly to facilitate the formation of an additional protective layer of aluminium oxide on treatment of the

- 10 -

coating and partly to avoid the possibility of elemental aluminium - which has a higher diffusivity in most metals than elemental platinum - diffusing into the metallic substrate.

Formation of the Intermetallic Diffusion Barrier

Following application of the coating to the metallic substrate, the coating may suitably be allowed to dry by evaporation of some or all of the components of the organic carrier, to leave on the surface of the metallic substrate a layer of metallic platinum and aluminium particles in intimate admixture in a desired molar ratio (eg about 1:2 Pt:Al). The dry residue from the organic carrier is preferably present at this stage, serving to anchor the metal particles in position for the subsequent reaction treatment to form the intermetallic diffusion barrier.

The deposited layer is then subjected to a reaction treatment which causes the platinum and the aluminium particles to form a platinum aluminide intermetallic diffusion barrier on the metallic substrate.

The reaction treatment typically includes the step of subjecting the coated metallic substrate to an elevated temperature for a time sufficient to form a platinum aluminide diffusion barrier. This temperature may be greater than about 200°C, for example greater than about 300°C. The temperature at which the reaction treatment takes place would normally be less than about 600°C, for example less than about 500°C. In an embodiment of the invention, the reaction treatment takes place at a temperature of about 400°C.

The above reaction treatment preferably takes place under a partial vacuum and/or in an inert atmosphere. By "inert atmosphere" is meant an atmosphere comprising at least about 90% inert gas or gases, eg nitrogen. Where a partial vacuum is used, the pressure may for example be less than about 10^{-4} Bar, preferably about 10^{-5} Bar. In one embodiment of the invention, sufficient atmospheric oxygen is present to form a relatively thin aluminium oxide scale on top of the platinum aluminide diffusion barrier.

- 11 -

The platinum aluminide diffusion barrier is preferably in the form of a surface layer overlying the metallic substrate, the layer being typically substantially homogeneous, continuous and of substantially uniform thickness. The thickness of the barrier may depend on factors such as the severity of the ambient conditions to which the protected metallic substrate will be exposed. The barrier preferably has a thickness of greater than about 1µm, for example greater than about 3µm, and up to about 20µm, for example less than about 10µm, eg an average thickness of about 5µm.

As mentioned above, the reaction treatment to form the platinum aluminide diffusion barrier from the coating may also cause the formation of an aluminium oxide scale on the surface of the diffusion barrier. This can further shield the metallic substrate from corrosive or oxidative agents.

The diffusion barrier formed according to the present invention may be overlay-coated by one or more further protective coatings, as will be readily apparent to those skilled in this art. For example, the platinum aluminide barrier layer may be subsequently overlay-coated with an 80/20 Ni/Cr oxidation resistant layer.

Industrial Applicability

The present invention provides an improved or at least alternative method for protecting metallic substrates (eg titanium alloys) against oxidation damage, particularly in high temperature oxidative or corrosive environments such as aero-engines.

The diffusion barrier according to the invention is found to be substantially inert and has sufficient strength and resistance to cracking to maintain its integrity under the wear and vibration conditions typically found in aero-engines. It does not interact adversely with the metallic substrate to an appreciable extent. It is also resistant to erosion and cracking under repeated cycling from low to high temperatures.

- 12 -

The above broadly describes the present invention without limitation. Variations and modifications as will be readily apparent to those skilled in this art are intended to be included in the scope of this application and any resultant patents.

- 13 -

CLAIMS

1. A method of forming a platinum aluminate diffusion barrier on a metallic substrate, the method comprising applying to the metallic substrate a coating comprising particulate platinum and particulate aluminium in an organic carrier and performing a reaction treatment on the thus applied platinum and aluminium which causes the platinum and the aluminium to form a diffusion barrier on the metallic substrate.
2. A method according to claim 1, wherein the metallic substrate comprises a titanium alloy.
3. A method according to claim 1 or claim 2, wherein the coating is applied in more than one step, whereby the coating is built up on the metallic substrate.
4. A method according to any one of the preceding claims, wherein the platinum particles and the aluminium particles are applied as the particles entrained in the organic carrier, as a single composition or sequentially as separate compositions.
5. A method according to any one of the preceding claims, wherein the organic carrier comprises relatively volatile components and relatively non-volatile components, whereby the organic carrier forms a dry residue on the metallic substrate after application, anchoring the platinum particles and the aluminium particles for the reaction treatment to form the diffusion barrier.
6. A method according to any one of the preceding claims, wherein the aluminium particles have an average effective diameter in the range of about 2 to about 10µm.

- 14 -

7. A method according to any one of the preceding claims, wherein the platinum particles have an average effective diameter in the range of about 2 to about 10 μ m.
8. A method according to any one of the preceding claims, wherein the reaction treatment comprises subjecting the platinum particles and the aluminium particles to a temperature in the range of about 200°C to about 600°C for a time sufficient to form a platinum aluminide diffusion barrier.
9. A method according to claim 8, wherein the reaction treatment takes place in an inert atmosphere.
10. An oxidation resistant structure comprising a metallic substrate and a platinum aluminide diffusion barrier disposed thereon, wherein the structure is formed by a method according to any preceding claim.
11. A structure according to claim 10, wherein the platinum aluminide diffusion barrier has a substantially uniform thickness over the major part of its area.
12. A structure according to claim 10 or 11, which comprises an aerospace component or a portion thereof.
13. An oxidation resistant aerospace component comprising a metallic substrate and a substantially uniform platinum aluminide diffusion barrier disposed thereon, wherein the diffusion barrier is continuous over an area of at least about 200 cm².
14. A structure or component according to any one of claims 10 to 13, wherein the platinum aluminide diffusion barrier has a thickness in the range of about 2 to about 10 μ m.

- 15 -

15. A component according to claim 13, when formed by a method according to any one of claims 1 to 9.



- 16 -

ABSTRACT**METHOD OF FORMING A DIFFUSION BARRIER
ON A METALLIC SUBSTRATE**

A method of forming a platinum aluminide diffusion barrier on a metallic substrate, eg a titanium alloy aerospace component, comprises applying to the metallic substrate a coating comprising particulate platinum and particulate aluminium in an organic carrier and performing a reaction treatment on the thus applied platinum and aluminium which causes the platinum and the aluminium to form an intermetallic diffusion barrier on the metallic substrate.

RECEIVED
THE PATENT OFFICE
21 OCT 2002

